



AQUEOUS BITUMEN

DESCRIPTION.

Kingfisher AQUEOUS BITUMEN is a blend of bitumen and flexible polymer in a water/solvent carrier.

It is a rubberised emulsion designed for use as a membrane for brick and concrete surfaces above and below ground and provides a tough, flexible, vapour proof barrier.

METHOD OF USE.

Surfaces to be treated can be damp but not waterlogged.

Two coats are applied where the material is being used in a sandwich construction.

The first priming coat should be thinned by adding 20% water to the product and mixing very thoroughly.

Allow to dry for 12 – 24 hours and then apply the second coat unthinned.

While damp, cover the coating with a thin layer of sharp sand to assist adhesion of final concrete screed.

Where a surface system is required, three coats are applied. A priming coat and two top coats of unthinned **Kingfisher AQUEOUS BITUMEN** of equal thickness.

Rate of Coverage – One square metre per litre.

Brushes should be washed out with water periodically during the application to large areas.

PRECAUTION.

Kingfisher AQUEOUS BITUMEN is non – flammable and safe in use. However as with all coatings and paints etc. it is advisable to avoid prolonged contact with the skin and splashes to the eyes and mouth should also be avoided.

It is recommended that protective gloves, glasses and overalls are worn during application.

In the case of contact with the skin, eyes and mouth the affected areas should be washed with clean water.

DO NOT apply at temperatures below 4°C.

Protect from frost.

Further Health and Safety information on this product is provided in the MSDS, copies of which are available from the Kingfisher Technical Dept. Tel 01229 869100 or Fax 01229 869101.