



POINTING MORTAR & POINTING SOLUTION

DESCRIPTION.

Kingfisher Pointing Mortar & Solution is a dry cement based powder premixed with appropriate proportions of sand and dyes to produce constant colour of mortar.

The product requires the addition of pointing solution diluted with water (1 to 5) to give a non-shrink, waterproof and decorative finish.

When used with Kingfisher Super Seal, it provides total water resistance. Also materials and workmanship can be guaranteed for 30 years when applied by an approved contractor.

COMPOSITION.

The pointing mortar is a mixture of high grade Portland Cement complying with BS 12 and selected Silica sands complying with BS1200. These are in the ration 1 to 3.4.

APPLICATION

Defective mortar should be removed to a minimum depth of 1.5 times the width of the joint. Brush and flush out loose material from joints with low pressure compressed air or water. leave joints damp. The product can be mixed either by hand or using a drill mixer attachment.

The powder should be added to the diluted pointing solution (1 to 5 water), ideally using a slow speed drill (400 – 600rpm) with Kingfisher mixer attachment.

The Kingfisher attachment does not entrain air into the solution thus eliminating the possibility of unnecessary shrinkage.

NOTE: The amount of liquid added should not exceed 4 litres per 25 kg bag of dry mortar.

Allow the mortar to stand for about 5 – 10 minutes to allow full saturation, and briefly remix, adding a small amount of liquid, as necessary to give optimum consistency.

If the facilities/tools for power mixing are unavailable then the mortar can be mixed by hand. Mix only small (5kg) quantities by adding powder to diluted pointing solution. Stir vigorously with a flat bladed trowel or paddle. Ensure contents are thoroughly mixed,

Allow the mixture to stand for 10 to 15minutes and then remix, adding extra liquid as required to give optimum consistency.

Fill Kingfisher Kwikpoint gun and use as instructed. Strike off excess to required shape when mortar has lost its sheen.

For further Health and Safety information on this product please refer to the Kingfisher Safety Data Sheet, copies of which are available from the Kingfisher Technical Dept. Tel. 01229 869100 or Fax 01229 868101.